

**DIRECT TO FILM
APPLICATION
INSTRUCTIONS**

Heavy/Firm Pressure

*****COLD PEEL*****

POLY 275F / 10 SEC


TRI-BLEND 275F / 10 SEC

50/50 300F / 12 SEC

COTTON 325F / 15 SEC

*****COLD PEEL*****

**REPRESS WITH PARCHMENT
PAPER FOR 8-10 SEC**



**Thank you for your
business!**

#BlingForEverybody

BlingForEverybody.com

info@blingforeverybody.com